



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: Donald R. Huffman, et al.

Examiner: Tsang Foster, S.N.

Serial No.: 08/236,933

Art Unit: 1745

Filed: May 2, 1994

Docket: 7913ZAZY

For: NEW FORM OF CARBON

Confirmation No.: 4115

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

DECLARATION OF ADAM DARWISH
PURSUANT TO 37 C.F.R. §1.132

Sir:

I, ADAM DARWISH, declare and say as follows:

1. I am currently a tutor of organic chemistry in the Chemistry Department at Sussex University, England. I was awarded a Ph.D. in Physical Organic Chemistry in 1992 and have continued working at Sussex University as a Research fellow until 1999, when I received a promotion to senior research fellow. I have conducted research in the area of fullerenes for several years. This research includes, but is not limited to, the preparation and purification of gram quantities of fullerenes, developing new fullerene-producing reactions, and improved chromatographic separation of C₆₀ and C₇₀. I am appending hereto an abbreviated version of my curriculum vitae, which summarizes my experience in the fullerene area.

2. In preparing this Declaration, I have read and reviewed the contents of USSN 08/236,933 in its entirety (" '933 application"), especially the description therein of the

preparation of fullerenes, including C₆₀ and C₇₀, and especially the procedure for separating the fullerenes from the soot described therein, especially in Example 1 thereof.

3. I was introduced to applicants' attorney by Dr. Harold Kroto.

4. I was requested by applicants' attorney to separate fullerenes, including C₆₀ and C₇₀, from the soot sample prepared by Dr. Terrones, which was forwarded to me.

5. The procedures described herein were either conducted by me or under my direct supervision and control.

6. The procedure used for separating the fullerenes from the soot utilized common separation techniques that were described in the '933 application or known and routine to one of ordinary skill in the art on August 30, 1990.

7. The same procedure was utilized for separating the fullerene from the soot produced at the lower pressure of 100 torr and at the higher pressure at 2 atm. More specifically, the samples of soot were extracted using a soxhlet extractor utilizing toluene as the solvent. Approximately, 10% of the soot sample was collected as soot extract. In the sample containing 1 gram of soot, i.e., the soot that was prepared from the vaporization of graphite at 100 torr using a current of about 100 amps, the soot extract was separated into the various fullerene fractions using preparative HPLC under the following conditions: Cosmosil 5μm PYE column (250mm x 10mm), HPLC-grade toluene as the solvent, eluted from the column at a rate of 4 ml/min. and the UV detector was set at 285 nm wavelength. Those fractions having an absorbance at 285 nm were collected. See Exhibit 2.

8. The fullerene fractions were then purified by recycling using the conditions described in Paragraph 7 herein.

9. A fullerene fraction, consisting of 65 mg of pure C₆₀ crystals, another fullerene fraction consisting of 15 mg of C₇₀ crystals and a third fullerene fraction of 7 mg of higher fullerenes comprised of C₇₆ (1.2 mg), C₇₈ (1.8 mg, two isomers) C₈₄ (2.5 mg), C₈₆ (0.5 mg), and C₉₀ (1.0 mg, two isomers) together with C₇₀O (2 mg), were collected from the 1 gram of soot prepared from the vaporization of graphite at 100 torr using a current of about 100 amp. Each of the fractions contained enough material to be seen with the naked eye.

10. The identity of each of the fullerenes in each of the fractions was verified by the mass spectra.

11. I have attached hereto copies of the mass spectra of each of the fullerenes isolated from the vaporization of graphite at 100 torr using a current of about 100 amps and the HPLC tracings of each isolated fullerene. In addition, I have attached the photographs of samples of each of the separated fullerenes dissolved in toluene and photographs of the crystals of each of these fullerenes obtained from evaporation of exactly the half volume of the toluene solution obtained except for C₈₆ where all the toluene solution was evaporated to dryness. (see Exhibits 3-12).

12. Exhibit 3 includes the mass spectrum of a sample of C₆₀ (3)(a) and the HPLC tracing of the C₆₀ fraction (3)(b). Exhibit 3 further includes a photograph of a sample of C₆₀ in solution in toluene (3)(c) and a photograph of the C₆₀ crystals obtained from the evaporation of the toluene (3)(d). The mass spectrum confirmed the identity of the C₆₀, and both the mass spectrum and the HPLC tracing showed that the product is quite pure. As indicated hereinabove, 65 mg of the C₆₀ crystals were recovered, which amount can be seen with the naked eye. Moreover, as further shown from the photograph in (3)(d), C₆₀ is present in sufficient amounts to be seen with the naked eye.

13. Exhibit 4 depicts the mass spectrum of the C₇₀ fraction (4)(a) and the HPLC tracing of the C₇₀ fraction (4)(b). The mass spectrum confirms the identity of C₇₀, while the mass spectrum and the HPLC tracing show that the sample is quite pure (Exhibit 4). Exhibit 4 further includes a photograph of a sample of the C₇₀ dissolved in toluene (4)(c) and a photograph of C₇₀ after evaporation of the toluene (4)(d). As indicated hereinabove, 15 mg of C₇₀ were collected, which also can be seen with the naked eye. As further shown by the photograph in Exhibit (4)(d), the C₇₀ crystals were present in sufficient amounts to be seen with the naked eye.

14. The remaining fullerenes ("higher fullerenes") were present in a total amount of 9 mg, and the higher fullerenes in total were present in amounts sufficient to be seen with the naked eye.

15. Exhibit 5 shows the mass spectrum of C₇₀O, the HPLC tracing of the product and a photograph of C₇₀O solution in toluene. Again, the mass spectrum confirms the identity of the product, while the mass spectrum and HPLC tracing show that it is quite pure.

16. Exhibit 6 depicts the mass spectrum of C₇₆, the HPLC tracing of C₇₆, and a photograph of C₇₆ in solution in toluene. From the mass spectrum and the HPLC tracing, the product is quite pure. The mass spectrum confirms the identity of the product.

17. Exhibit 7 depicts the mass spectrum of C₇₈, the HPLC tracing of the two isomers of C₇₈ that were obtained from the soot, and a photograph of C₇₈ in solution in toluene. The mass spectrum confirms that the product is C₇₈, and the HPLC tracing clearly shows that 2 isomers were formed.

18. Exhibit 8 depicts the mass spectrum of C₈₄, the HPLC tracing of C₈₄ and a photograph of C₈₄ dissolved in toluene. The mass spectrum confirms the identity of the product as C₈₄ and the mass spectrum and the HPLC tracing show that the product is quite pure.

19. Exhibit 9 depicts the mass spectrum of C_{86} , the HPLC tracing of same, and a photograph of C_{86} dissolved in toluene. The identity of the product is confirmed by the mass spectrum, and the mass spectrum and the HPLC tracing show that the product is quite pure.

20. Exhibit 10 depicts the mass spectrum of C_{90} , the HPLC tracing of two isomers of C_{90} and a photograph of C_{90} dissolved in toluene. The mass spectrum confirmed the identity of the product and the HPLC tracing shows that two isomers of C_{90} were collected.

21. Exhibit 11 is a photograph of various fullerenes, i.e., C_{60} , C_{70} , C_{76} , C_{78} , C_{84} , C_{86} , and C_{90} (that were obtained from the soot produced from the vaporization of graphite at 100 torr) dissolved in toluene.

22. Exhibit 12 consists of photographs of higher fullerene products, which were isolated from the soot produced from the vaporization of graphite at 100 torr, in solution in toluene and the solids of same obtained from the evaporation of exactly the half volume of the toluene solution obtained except for C_{86} where all the toluene solution was evaporated to dryness. The bottom portion of Exhibit 12 depicts each of these higher fullerene products. As can be seen by the photographs, the C_{76} , C_{78} , C_{84} , C_{86} and C_{90} produced from the soot obtained from the vaporization of graphite at 100 torr can be seen with the naked eye.

23. I also separated the second sample comprised of 100 mg. of soot that was produced at the higher pressure of 2 atm using the same technique as described in Paragraphs 7 and 8. Toluene (100 ml) was used as the solvent for extraction using a soxhlet extractor, and 9 mg or 9% yield was obtained. The various products obtained from this soot are described in Paragraphs 24-26.

24. Attached as Exhibit 13 is the mass spectrum of C_{60} and photographs of a sample of C_{60} in solution in toluene obtained from the soot produced from the vaporization of graphite at

2 atm and the C₆₀ crystals obtained from the evaporation of the toluene. The mass spectrum confirmed the identity of C₆₀. As shown by the photograph in Exhibit 13, the C₆₀ isolated (5.0 mg) from the 100 mg. of soot received from Dr. Terrones can be seen with the naked eye.

25. Attached as Exhibit 14 is the mass spectrum of C₇₀, and the photographs of a sample of C₇₀ in solution in toluene obtained from the soot produced from the vaporization of graphite at 2 atm and C₇₀ crystals (1.5 mg) obtained from the evaporation of the toluene. Again, as shown by the photograph, the C₇₀ isolated from the 100 mg. of soot, which was sent by Dr. Terrones, can be seen with the naked eye.


26. Exhibit 15 depicts the mass spectrum of the higher fullerenes obtained when the vaporization of graphite was performed at 2 atm. The mass spectrum depicts that higher fullerenes up to C₁₀₄ were detected by the mass spectrum. Exhibit 15 also depicts the photographs of a sample of higher fullerenes in solution in toluene and photographs of the crystals of the higher fullerenes (1.0 mg) obtained after evaporation of toluene. Thus, the higher fullerenes in total were present in the soot obtained from the vaporization of graphite at 2 atm in amounts sufficient to be seen with the naked eye.

27. Exhibit 16 consists of photographs of separate samples of C₆₀, C₇₀ and the higher fullerenes, isolated from the soot prepared from the vaporization of graphite at 2 atm and 100 amps, dissolved in toluene and photographs of the crystals of C₆₀, C₇₀ and the higher fullerenes obtained from evaporation of the toluene therefrom. Thus, as shown by the photographs, these crystals of C₆₀, C₇₀ and higher fullerenes can be seen with the naked eye.

28. I further declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true and further that these statements were made with the knowledge that willful false statements and the like so

made are punishable by fine or imprisonment or both under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Date: August 28, 2007


Adam Darwish

Curriculum Vitae

Name: Adam Darwish

Date of Birth: 7th March 1958

Gender: Male

Nationality: British

Marital Status: Married

Address: 15 Sunnydale Avenue, Patcham, Brighton, East Sussex, BN1 8NR

Tel No.: (Home) 01273 501522
(Mobile) 07810768880

E-mail: kapg2@sussex.ac.uk

EDUCATION

D.Phil Physical Organic Chemistry (Sussex University, 1989-1992, UK)

BSc. Chemistry (Yarmouk University, 1977-1980, Jordan)

RESEARCH EXPERIENCE

2006-Present Tutor of Organic Chemistry, Chemistry Department, Sussex University.

1999-2006 Senior Research Fellow, Chemistry Department, Sussex University.

1992-1999 Research Fellow, Chemistry Department, Sussex University

Research involved the preparation and purification of gram quantities of fullerenes, and development of a new fullerene-producing reactor together with improved chromatographic separation of C₆₀ and C₇₀. Carrying out a number of studies into new chemical reactions of C₆₀, C₇₀, C₇₆, C₇₈ and C₈₄ and fluorinated fullerenes (C₆₀F₁₈, C₆₀F₁₈O_x and C₆₀F₂₀). These included reduction, oxidation, fluorinations, additions, electrophilic and nucleophilic addition/substitutions, which have resulted in a large number of publications (**71 publications**) in a variety of scientific journals.

1989-1992 D.Phil research student (gas phase elimination of some nitrogen-containing heteroaromatics)

SELECTED PUBLICATIONS

1. Fullerenes, **Adam D. Darwish**, *Annu. Rep. Prog. Chem., Sect. A: Inorg. Chem.*, 2007, **103**, 370 – 391.
2. Pyrolytic Trifluoromethylation of [76]-, [78]-, [84]-, and Aza[60]Fullerene with silver Trifluoroacetate; Evidence for Coordination of Fullerenes to Silver, **Adam D. Darwish**, A. K. Abdul-Sada, and R. Taylor, *Fullerene, Nanotubes, and Carbon Nanostructures*, 2006, **14**(1), 111.
3. Isolation of Two Seven-membered Ring C₅₈ Fullerene Derivatives: C₅₈F₁₇CF₃ and C₅₈F₁₈. P. A. Troshin, A. G. Avent, **A. D. Darwish**, N. Martsinovich, A. K. Abdul-Sada, J. M. Street and R. Taylor, *Science*, 2005, **309**, 278.
4. Electrophilic Substitution by the Fluorofullerene C₆₀F₁₈, **A. D. Darwish**, A. G. Avent, A. K. Abdul-Sada, I. V. Gol'dt, I. Kuvytchko, P. B. Hitchcock and R. Taylor, *Chem Eur. J.*, 2004, **10**, 4523.
5. Electrophilic Substitution of C₆₀F₁₈ into Phenols: HF Elimination Between OH and a 1,3-Shifted Fluorine Giving Benzofurano[2',3':10,26]hexadecafluoro[60]fullerene and Derivatives, **A. D. Darwish**, A. G. Avent, J. M. Street and R. Taylor, *Org. Biomol. Chem.*, 2003, **1**, 1764.
6. C₆₀F₂₀: "Saturnene", an Extraordinary Squashed Fullerene. O. V. Boltalina, V. Yu. Markov, P. A. Troshin, **A. D. Darwish**, J. M. Street and R. Taylor, *Angew. Chem. Int. Ed.*, 2001, **40**, 787.
7. Novel Base-Catalysed Formation of Benzo[b]furano[60]- and -[70]Fullerenes. **A.D. Darwish**, A.G. Avent, H.W. Kroto, R. Taylor and D.R.M. Walton, *J. Chem Soc., Perkin Trans. 2*, 1999, 1983.
8. Hydrogenation of [76]-, [78]- and [84]Fullerenes. **A.D. Darwish**, H.W. Kroto, R. Taylor and D.R.M. Walton, *J. Chem Soc., Perkin Trans. 2*, 1996, 1415.
9. Preparation and ¹³C NMR Spectroscopic Characterization of C₆₀Cl₆. P.R. Birkett, A.G. Avent, **A.D. Darwish**, H.W. Kroto, R. Taylor and D.R.M. Walton, *J. Chem Soc., Chem. Commun.*, 1993, 1230.



a




b



c

- a. Soxhlet extractor**
- b. Soot extract in 100ml of toluene**
- c. Concentrated soot extract in 30ml of toluene**

File: JADAX IDENT: 33 Acq: 19-MAY-2007 13:16:04 +4102 Cal: CALL
 Autospec B: + Modest BP1: 42484332 TIC: 848652326 Flags: HALL
 File Type: 7.5 MIN C60
 1800 720




a

- a. Mass spectra of C₆₀
- b. HPLC traces (7.5 minute)
- c. C₆₀ solution in toluene
- d. C₆₀ crystals


[REDACTED]

3



DARWISH EXHIBIT 5

File: SADA Ident: 23 Acq: 12-AUG-2007 13:31:41 +2156 Cal: CALI
 Auraspac E1: Magnet Bp1: 0471752 T1C: 63708848 Flag: 1EALL
 File Text: 13.3MIN
 100% 340




a

- a. Mass spectra of $C_{70}O$.
- b. HPLC traces (13.3 minutes.)
- c. $C_{70}O$ solution in toluene


b

c


File: TADAN Ident17 Acq:19-AUG-2007 12:45:14 .6.59 Cal:CALL
 Autospec EI; Negative Split:619318 TIC:5693920 Flag:HALL
 File: TADAN12.1 MW C76
 1004



a



b




c


- a. Mass spectra of C_{76}
- b. HPLC traces (15.3 min.)
- c. C_{76} solution in toluene

DARWISH EXHIBIT 7

91052004 1000110 Acq:19-AUG-2007 12:51:17 +1:14 Cal:CAL1
Autocore 81, Nozzle Hpl0016501 TIC:02714150 Plog:FULL
File T00110.4 MIN C78



a



b




c

- a. Mass spectra of C₇₈
- b. HPLC traces (16.4 & 16.7.3 min.), two isomers
- c. C₇₈ solution in toluene.

DARWISH EXHIBIT 8

File: GADAM I00017 ACQ: 19-AUG-2007 12:54:32 -0:52 CALICALL
Autospec EI+ Magnet Sp: 0203715 YIC130615262 P199: HALL
File Text: 20.5 MIN C84
1000





a

b

c

- a. Mass spectra of C_{84}
- b. HPLC traces (20.5 min.)
- c. C_{84} solution in toluene

File:INABUS Ident:0 Acq:72-AUG-2007 13:36:45 +044 Cal:CAL1
 Aufschnee St. Magnet Det:4925172 File:61463408 Flags:HALD
 File Text:24.8 MIN
 720
 1924




90


6

- a. **Mass spectra of C₈₆**
- b. **HPLC traces (24.8 minutes)**
- c. **C₈₆ solution in toluene**

PL101821001 Ident:10 A-9:19-AUG-2007 13:01:39 11:21 Cal:CALL
Autocorrec: E1. Magnets BPI:989877 TIC:45129100 PLAGH-HALL
File 101821001.48 MTR C90 719 x15.00



a




b




c

- a. Mass spectra of C₉₀
- b. HPLC traces (29 & 31 minutes), two isomers
- c. C₉₀ solution in toluene


DARWISH EXHIBIT 11



C₆₀ C₇₀ C₇₆ C₇₈ C₈₄ C₈₆ C₉₀




C70 O C76 C78 C84 C86 C90



C70 O C76 C78 C84 C86 C90



File: 17ADAM Ident: 9 Acq: 25-AUG-2007 15:31:45 +1:12 Cal: CAL1
 AugSpec Bl: Magnet BPl: 29737676 TIC: 320138496 Plags: HALL
 File Text: C60/S2



Mass spectra of C₆₀

C₆₀ solution in toluene
 C₆₀ crystals

File: 15ADAK Ident: 16 Acq: 25-AUG-2007 19:22:03 +2:05 Cal: CALI
 Autospec Hi-Magnet Bp1: 52487024 TIC: 593338688 Plase: HALL
 File Text: C70 / B2
 100%




C70

Mass spectra of C70

C70 solution in toluene
 C70 crystals

DARWISH EXHIBIT 15

File: 13ADAM Ident: 22 Acq: 25-AUG-2007 15:05:52 +2:48 Cal: GALL
Autospec SI- Magnet BPT: 50094684 TIC: 361265472 P1ags: WALL
File Text: HE/B2
100% 840 100% x3.00



Mass spectra of H.F's up
to C₁₀₄

H.F's solution in toluene
H.F's crystals

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

13-1-1971

000

000

000

